

MDPE

R906U

MDPE for rotational molding

Application

Rotational molding, Medium/large container, Tank, Outdoor structure

Characteristics

Excellent processability, High impact strength, UV stability, Stress-cracking resistance

Physical properties

Item	Test Method	Unit	Typical Value
Melt index	ASTM D1238	g/10min	6.0
Density	ASTM D1505	g/cm ³	0.936
Tensile strength(at break)	ASTM D638	kg/cm ²	200
Elongation (at break)	ASTM D638	%	>500
Flexural modulus	ASTM D790	kg/cm ²	6,000
Izod Impact Strength	ASTM D256	kg cm/cm	Non-Break
Vicat softening point	ASTM D1525	°C	114
Brittleness temperature	ASTM D746	°C	<-80
Shore hardness	ASTM D2240	D Scale	54
Stress-cracking resistance	ASTM D1693	hrs	>200

Note) Data shown above are representative values for reference purposes only, and not to be construed as specifications.

Contact information

Hanwha TotalEnergies Petrochemical co. Ltd.
www.htpchem.com

Sales Office
04525 No.92, Sejong-daero, Jung-gu, 16,18-20F, Hanwha
Finance Plaza, Seoul, Republic of Korea
16th floor of Hanwha Financial Plaza

Customer Technical Service
31900 103, Dokgot 2-ro, Daesan-eup, Seosan-si,
Chungcheongnam-do, Republic of Korea
T. 041-660-6190 F. 041-660-6189

Disclaimer

This document is copyrighted by Hanwha TotalEnergies Petrochemical. All information is for reference only and is not the specifications of the final product. Customers should make their own judgments as to whether our products and information serve a particular purpose and what regulations apply to customers' use of such products. Hanwha TotalEnergies Petrochemical is not responsible or obligated for the contents of this document. Hanwha TotalEnergies Petrochemical provides no warranties of any kind, either express or implied (such as merchantability and or fitness for a particular purpose, etc.) with respect to any information contained in this material. Hanwha TotalEnergies Petrochemical may arbitrarily change the contents of this material without prior notice.