HDPE

B220A

HDPE for blow molding

Application

Blow molding, Small container, Food container, Chemicals

Characteristics

Excellent surface properties, Stress-cracking resistance

Physical properties

Item	Test Method	Unit	Typical Value
Melt index	ASTM D1238	g/10min	0.35
Density	ASTM D1505	g/㎤	0.959
Tensile strength (at yield)	ASTM D638	kg/㎠	280
Tensile strength(at break)	ASTM D638	kg/㎠	320
Elongation (at break)	ASTM D638	%	>500
Flexural modulus	ASTM D790	kg/㎠	11000
Izod Impact Strength (23℃)	ASTM D256	kg ㎝/㎝	12
Vicat softening point	ASTM D1525	℃	123
Melt temperature	HTC Method	℃	132
Brittleness temperature	ASTM D746	℃	<-80
Stress-cracking resistance	ASTM D1693	(F50)	>500
Rockwell hardness	ASTM D785	R scale	55
Flammability	UL94	1/16”	HB

Note) Data shown above are representative values for reference purposes only, and not to be construed as specifications.

Processing conditions

Item	Unit	Typical value
Hopper unit	℃	Room Temp.
Cylinder (supply and compression unit)	℃	140 ~ 170
Cylinder (measurement unit) and die unit	℃	160 ~ 200

The actual temperature depends on the design of the screw and die, the size and thickness of the molded article, and the amount of extrusion during processing. In particular, when processed at a temperature above 220°C, the physical properties are greatly degraded due to the characteristics of hollow molded products that use a lot of scraps, so please be careful.

Certification

Hanwha TotalEnergies Petrochemical B220A satisfies the 21 CFR 177.1520 regulations, the food packaging standards of the U.S. Food and Drug Administration (FDA).
For further inquiries, please contact Customer Technical Service.

Contact information

Hanwha TotalEnergies Petrochemical co. Ltd.
www.htpchem.com

Sales Office
04525 No.92, Sejong-daero, Jung-gu, 16,18-20F, Hanwha Finance Plaza, Seoul, Republic of Korea
16th floor of Hanwha Financial Plaza

Customer Technical Service
31900 103, Dokgot 2-ro, Daesan-eup, Seosan-si, Chungcheongnam-do, Republic of Korea
T. 041-660-6190 F. 041-660-6189