

# HDPE

## P300A

### HDPE for wires & cable

#### Application

Wire & cable, Optical cables, Semi-conductive shield application (outer layer)

#### Characteristics

Excellent low-speed crack resistance, Excellent processability

#### Physical properties

Item	Test Method	Unit	Typical Value
Melt index	ISO R1133 (190°C, 5kg )	g/10min	0.65
Density	ISO R1183	g/cm <sup>3</sup>	0.947
Oxidation induction time (OIT)	ISO R11357-6 (OIT, 200°C)	Minute	≥40
Thermal conductivity (60°C)	HTC Method	W/m <sup>2</sup> K	0.35
Thermal expansion coefficient (40°C)	HTC Method	m/m <sup>2</sup> K	0.00017
Tensile modulus	ISO R527	MPa	850
Tensile strength (at yield)	ISO R527	MPa	23
Elongation (at break)	ISO R527	%	≥350
Flexural modulus	ISO R178	MPa	750
FNCT (Arkopal, 80°C, 4.0MPa)	ISO R16770	hrs	≥2000
Charpy impact strength (0°C)	ISO R868	kJ/m <sup>2</sup>	20

Note) Data shown above are representative values for reference purposes only, and not to be construed as specifications.

#### Contact information

Hanwha TotalEnergies Petrochemical co. Ltd.  
www.htpchem.com

Sales Office  
04525 No.92, Sejong-daero, Jung-gu, 16,18-20F, Hanwha  
Finance Plaza, Seoul, Republic of Korea  
16th floor of Hanwha Financial Plaza

Customer Technical Service  
31900 103, Dokgot 2-ro, Daesan-eup, Seosan-si,  
Chungcheongnam-do, Republic of Korea  
T. 041-660-6190 F. 041-660-6189

#### Disclaimer

This document is copyrighted by Hanwha TotalEnergies Petrochemical. All information is for reference only and is not the specifications of the final product. Customers should make their own judgments as to whether our products and information serve a particular purpose and what regulations apply to customers' use of such products. Hanwha TotalEnergies Petrochemical is not responsible or obligated for the contents of this document. Hanwha TotalEnergies Petrochemical provides no warranties of any kind, either express or implied (such as merchantability and or fitness for a particular purpose, etc.) with respect to any information contained in this material. Hanwha TotalEnergies Petrochemical may arbitrarily change the contents of this material without prior notice.