

# PP

## HU300

### High stiffness homo PP for BOPP film

#### Application

Film, BOPP film, Food packaging film

#### Characteristics

High stiffness, High thermal resistance, Excellent processability

#### Physical properties

Item	Test Method	Unit	Typical Value
Melt index	ASTM D1238	g/10min	3
Density	ASTM D1505	g/cm <sup>3</sup>	0.91
Tensile strength (at yield)	ASTM D638	kg/cm <sup>2</sup>	420
Elongation (at break)	ASTM D638	%	400
Flexural modulus	ASTM D790	kg/cm <sup>2</sup>	20000
Izod Impact Strength (23°C)	ASTM D256	kg cm/cm	3
Rockwell hardness	ASTM D785	R scale	100
Heat deflection temperature	ASTM D648	°C	117

Note) Data shown above are representative values for reference purposes only, and not to be construed as specifications.

#### Film properties

Item	Test Method	Unit	Typical value
Thickness	-	μm	30
Tensile strength MD	ASTM D882	kg/cm <sup>2</sup>	1,500
Tensile strength TD	ASTM D882	kg/cm <sup>2</sup>	2,800
Tensile modulus (MD)	ASTM D882	kg/cm <sup>2</sup>	23,000
Tensile modulus (TD)	ASTM D882	kg/cm <sup>2</sup>	35,000

#### Certification

Hanwha TotalEnergies Petrochemical HU300 satisfies the 21 CFR 177.1520 regulations, the food packaging standards of the U.S. Food and Drug Administration (FDA).

For further inquiries, please contact Customer Technical Service.

## Contact information

Hanwha TotalEnergies Petrochemical co. Ltd.  
[www.htpchem.com](http://www.htpchem.com)

Sales Office  
04525 No.92, Sejong-daero, Jung-gu, 16,18-20F, Hanwha  
Finance Plaza, Seoul, Republic of Korea  
16th floor of Hanwha Financial Plaza

Customer Technical Service  
31900 103, Dokgot 2-ro, Daesan-eup, Seosan-si,  
Chungcheongnam-do, Republic of Korea  
T. 041-660-6190 F. 041-660-6189

### Disclaimer

This document is copyrighted by Hanwha TotalEnergies Petrochemical. All information is for reference only and is not the specifications of the final product. Customers should make their own judgments as to whether our products and information serve a particular purpose and what regulations apply to customers' use of such products. Hanwha TotalEnergies Petrochemical is not responsible or obligated for the contents of this document. Hanwha TotalEnergies Petrochemical provides no warranties of any kind, either express or implied (such as merchantability and or fitness for a particular purpose, etc.) with respect to any information contained in this material. Hanwha TotalEnergies Petrochemical may arbitrarily change the contents of this material without prior notice.