

HDPE

F120U

HDPE for Film

Application

Agricultural film, Mulching film

Characteristics

Excellent mechanical properties, Excellent processability, Weather resistance, Low Fisheye, Die build-up

Physical properties

Item	Test Method	Unit	Typical Value
Melt index	ASTM D1238	g/10min	0.05
Density	ASTM D1505	g/cm ³	0.956
Tensile strength (at yield)	ASTM D638	kg/cm ²	230
Tensile strength(at break)	ASTM D638	kg/cm ²	300
Elongation (at break)	ASTM D638	%	>500
Flexural modulus	ASTM D790	kg/cm ²	10000
Brittleness temperature	ASTM D746	°C	<-80

Note) Data shown above are representative values for reference purposes only, and not to be construed as specifications.

Film properties

Item	Test Method	Unit	Typical value
Tensile strength at break (MD)	ASTM D882	kg/cm ²	650
Tensile strength at break (TD)	ASTM D882	kg/cm ²	550
Elongation at break (MD)	ASTM D882	%	440
Elongation at break (TD)	ASTM D882	%	640
Elmendorf tear strength (MD)	ASTM D1922	kg/cm ²	7
Elmendorf tear strength (TD)	ASTM D1922	kg/cm ²	260
Dart drop impact strength	ASTM D1709	g	> 200

Note) The above data is a representative value of the guide material and can be changed according to the processing conditions with a Φ50mm extruder, expansion ratio of 5.0, and thickness of 20 μm.

Certification

Hanwha TotalEnergies Petrochemical are limitations in applying Hanwha TotalEnergies F120U for food packaging purposes.

For further inquiries, please contact Customer Technical Service.

Contact information

Hanwha TotalEnergies Petrochemical co. Ltd.
www.htpchem.com

Sales Office
04525 No.92, Sejong-daero, Jung-gu, 16,18-20F, Hanwha
Finance Plaza, Seoul, Republic of Korea
16th floor of Hanwha Financial Plaza

Customer Technical Service
31900 103, Dokgot 2-ro, Daesan-eup, Seosan-si,
Chungcheongnam-do, Republic of Korea
T. 041-660-6190 F. 041-660-6189

Disclaimer

This document is copyrighted by Hanwha TotalEnergies Petrochemical. All information is for reference only and is not the specifications of the final product. Customers should make their own judgments as to whether our products and information serve a particular purpose and what regulations apply to customers' use of such products. Hanwha TotalEnergies Petrochemical is not responsible or obligated for the contents of this document. Hanwha TotalEnergies Petrochemical provides no warranties of any kind, either express or implied (such as merchantability and or fitness for a particular purpose, etc.) with respect to any information contained in this material. Hanwha TotalEnergies Petrochemical may arbitrarily change the contents of this material without prior notice.