

J810



HDPE

HDPE for injection

Application

Injection molding, Household goods parts, Electrical and electronic parts, Industrial materials component

Characteristics

Physical properties

High flowability, Thermal resistance stability, Excellent mechanical properties

ltem	Test Method	Unit	Typical Value
Melt index	ASTM D1238	g/10min	7.0
Density	ASTM D1505	g/cm³	0.951
Tensile strength (at yield)	ASTM D638	kg/cm²	250
Flexural modulus	ASTM D790	kg/cm²	12000
Elongation (at break)	ASTM D638	%	>300
Vicat softening point	ASTM D1525	°C	122
Melt temperature	HTC Method	°C	130
Brittleness temperature	ASTM D746	°C	<-80
Rockwell hardness	ASTM D785	R scale	60

Note) Data shown above are representative values for reference purposes only, and not to be construed as specifications.

Certification

Contact information Hanwha TotalEnergies Petrochemical are limitations in applying Hanwha TotalEnergies J810A for food packaging purposes.

For further inquiries, please contact Customer Technical Service.

Hanwha TotalEnergies Petrochemical co. Ltd. www.htpchem.com Sales Office 04525 No.92, Sejong-daero, Jung-gu, 16,18-20F, Hanwha Finance Plaza, Seoul, Republic of Korea 16th floor of Hanwha Financial Plaza

Customer Technical Service 31900 103, Dokgot 2-ro, Daesan-eup, Seosan-si, Chungcheongnam-do, Republic of Korea T. 041-660-6190 F. 041-660-6189

Disclaimer

This document is copyrighted by Hanwha TotalEnergies Petrochemical. All information is for reference only and is not the specifications of the final product. Customers should make their own judgments as to whether our products and information serve a particular purpose and what regulations apply to customers' use of such products. Hanwha TotalEnergies Petrochemical is not responsible or obligated for the contents of this document. Hanwha TotalEnergies Petrochemical provides no warranties of any kind, either express or implied (such as merchantability and or fitness for a particular purpose, etc.) with respect to any information contained in this material. Hanwha TotalEnergies Petrochemical may arbitrarily change the contents of this material without prior notice.